

#### Auckland

82 Henderson Valley Rd Henderson P 09 8360124 f 09 8360103 e - auck@bbstimbers.co.nz

## Whangarei

27 Kioreroa Rd Whangarei p 09 4389358 f 09 4300455 e- office@bbstimbers.co.nz

#### Christchurch

14 Halwyn Drive Hei Hei p 03 3445591 f 03 3445592 e- chch@bbstimbers.co.nz

# Ash (Australian)

#### Specification sheet

Other Name(s): Victorian Ash, Alpine Ash, Mountain Ash,

Tasmanian Oak

**Scientific Name:** Eucalyptus delegatensis ,Eucalyptus regnans

Distribution: Australia

Average Dried Weight: 660 kg/M3

**Durability:** Moderately Durable

Janka Hardness: (5.7 kN)

Modulus of Rupture/Bending

Strength (109 MPa)

Modulus of Elasticity/ stiffness: (14.8GPa)

Strength: SD6

# **VICTORIAN ASH**

## Seasoning:

- Difficult to dry.
- Requires a long period of air seasoning.

#### Characteristics:

- These timbers are quarter sawn to facilitate drying.
- The colour ranges from light beige to light brown with sometimes a pink tint.
- The grain is usually straight but sometimes interlocked or wavy.
- Such material often produces an attractive fiddle-back figure.

#### Working Qualities:

- The timber saws and machines well.
- Re-sawing or deep cutting is not to be recommended.
- Finishes well and can be glued, screwed, stained and polished satisfactorily.

#### Uses:

Cabinet making, joinery and flooring.

# **Product Attributes:**

- All quarter sawn.
- Veneers available.
- Usually straight grained.
- Fixed widths available.
- · Light beige to light brown, sometimes with a pink tint.
- Machines well, Long lengths available.

#### **Product Limitations**

- Gum streaks are a regular occurrence.
- Variations in colour.