

Auckland

82 Henderson Valley Rd Henderson P 09 8360124 f 09 8360103 e - auck@bbstimbers.co.nz

Whangarei

27 Kioreroa Rd Whangarei p 09 4389358 f 09 4300455 e– office@bbstimbers.co.nz

Christchurch

14 Halwyn Drive Hei Hei p 03 3445591 f 03 3445592 e– chch@bbstimbers.co.nz

Macrocarpa: USA

Specification Sheet



Other Name(s): Monterey Cypress

Scientific Name: Cupressus macrocarpa

<u>Distribution:</u> USA

Average Dried Weight: 485 kg/M3

Durability: Moderately Durable

Janka Hardness: (2.8 kN)

Modulus of Rupture/Bending

Strength (78.4 MPa)

Modulus of Elasticity/ stiffness: (7.6 GPa)

Macrocarpa

Seasoning:

- It is difficult to kiln dry with cell collapse and checking.
- · Low shrinkage factor.

Characteristics:

- A honey brown coloured wood, with a fine even texture.
- It is quite a stiff/strong timber when dry.
- · Stable.
- · Beautifully scented

Working Qualities:

- The timber is easily worked and finishes excellently.
- It can be glued, stained, polished and varnishes well.

Uses:

Exterior joinery, boat building, cabinet work and veneers.

Product Attributes:

- Naturally resistant to insect & fungal attack
- · Machines and turns very well.
- Veneers available.
- Fixed widths Available

Product Limitations

• Difficult to dry.