

Auckland

82 Henderson Valley Rd Henderson P 09 8360124 f 09 8360103 e - auck@bbstimbers.co.nz

Whangarei

27 Kioreroa Rd Whangarei p 09 4389358 f 09 4300455 e- office@bbstimbers.co.nz

Christchurch

14 Halwyn Drive Hei Hei p 03 3445591 f 03 3445592 e- chch@bbstimbers.co.nz

Purpleheart (Central American)

Specification sheet



Other Name(s): Amaranth, Violet Wood

Scientific Name: Peltoyne spp.

<u>Distribution:</u> Central America

Average Dried Weight: 905 kg/M3

Durability: Very Durable

Janka Hardness: 11.19 (kN)

Modulus of Rupture/Bending

Strength (151.7 MPa)

Modulus of Elasticity/ stiffness: (20.26 GPa)

Strength: 9 (on scale 1-10)

Seasoning:

.• Dries fairly rapidly with little degrade.

But care is needed to dry out the centre of thick pieces.

Characteristics:

- The heartwood is a deep purple-violet colour when freshly cut, maturing to dark brown.
- The original colour is restored when re-cut.
- Straight grained, but often irregular, wavy and sometimes interlocked, producing a pleasing striped figure on quartered surfaces.
- Texture moderate to fine.

Working Qualities:

- Wood turns well and smoothly.
- Pre-bore for nailing, glues without difficulty and stains and wax polishes easily.
- Spirit finishes remove the purple colour.

Uses:

- Although expensive, it is used for heavy constructional work, bridge building, fresh water piling, dock work, cladding, house construction and vats.
- Excellent for flooring and very suitable for gymnasium equipment, shafts, tool handles, boat building, turnery, furniture and billiard tables.
- Also as decorative veneers for inlaying and marguetry work etc.
- Best colour from sawcut as steaming affects the soluble phonicoin content.

Product Attributes:

- Large sizes available.
- No bleeding of stain.