

Auckland

#### Whangarei

82 Henderson Valley Rd Henderson P 09 8360124 f 09 8360103 e - auck@bbstimbers.co.nz 27 Kioreroa Rd Whangarei p 09 4389358 f 09 4300455 e- office@bbstimbers.co.nz

#### Christchurch

14 Halwyn Drive Hei Hei p 03 3445591 f 03 3445592 e- chch@bbstimbers.co.nz

Specification sheet

# Saligna (Australia , New Zealand)



/	•
Other Name(s):	Sydney Blue Gum
Scientific Name:	Eucalyptus saligna
Distribution:	Australia, New Zealand
Average Dried Weight:	920 kg/M3
Durability:	Moderately Durable
Janka Hardness:	18 (kN)
<u>Modulus of Rupture/Bending</u> <u>Strength</u>	( 140 MPa)
Modulus of Elasticity/ stiffness:	(18 GPa)
Strength:	8 ( on scale 1-10 )

## SALIGNA

#### Seasoning:

Difficult to dry as prone to surface checking.

#### Characteristics:

- The colour ranges from light to dark pink.
- The grain is usually interlocked, occasionally straight.
- The texture is coarse.
- To facilitate drying the timber is always quarter sawn.

## Working Qualities:

- The timber works fairly well but it is rather difficult to obtain a smooth surface unless the cutting angle is reduced to 20°.
- It nails and screws fairly well.
- Stains and polishes reasonably well.

#### Uses:

• Joinery and construction.

#### **Product Attributes:**

- Good lengths available.
- Veneers available.
- Machines reasonably well with care.
- Takes stains and polishes well.
- Fixed widths.
- Light pink to dark pink

## **Product Limitations:**

- Variable in colour.
- Grain usually interlocked with a coarse texture.