

#### **Auckland**

82 Henderson Valley Rd Henderson P 09 8360124 f 09 8360103 e - auck@bbstimbers.co.nz

## Whangarei

27 Kioreroa Rd Whangarei p 09 4389358 f 09 4300455 e- office@bbstimbers.co.nz

### Christchurch

14 Halwyn Drive Hei Hei p 03 3445591 f 03 3445592 e- chch@bbstimbers.co.nz

# Zebrano (West Africa)



**7**ebrawood

**Scientific Name:** 

Microberlinia brazzavillensis

Specification sheet

**Distribution:** 

West Africa

**Average Dried Weight:** 

820 kg/M3

**Durability:** 

Durable

Janka Hardness:

8.1 (kN)

Modulus of Rupture/Bending

Strength

(123 MPa)

Modulus of Elasticity/ stiffness: (16.37 GPa)

Strength:

8+ (on scale 1-10)

# Seasoning:

**ZEBRANO** 

Dries slowly with a tendency to surface check.

#### Characteristics:

- The heartwood is golden brown, with narrow-veining or streaks of dark brown to almost black giving a zebra stripe appearance.
- It is fairly hard with good toughness and impact properties.

# Working Qualities:

- Easily worked although interlocked grain can cause some planning problems.
- Glues, sands, stains and polishes well.

## Uses:

Fine furniture, flooring and interior decoration.

## **Product Attributes:**

- Distinctive unique grain.
- Easily worked with care.
- Takes stains and polishes well.
- Golden, yellow-brown with narrow streaks of dark black / brown.
- Veneers available.

#### **Product Limitations:**

- Interlocked grain can cause problems.
- Variable in supply •
- Very opened grained.
- Needs clear filling.
- No fixed widths.

