

Auckland

#### Whangarei

82 Henderson Valley Rd Henderson P 09 8360124 f 09 8360103 e - auck@bbstimbers.co.nz 27 Kioreroa Rd Whangarei p 09 4389358 f 09 4300455 e- office@bbstimbers.co.nz

#### Christchurch

14 Halwyn Drive Hei Hei p 03 3445591 f 03 3445592 e- chch@bbstimbers.co.nz

**Specification Sheet** 

# Alaskan Yellow Cedar: North West USA



<u>Other Name(s):</u> Scientific Name:	Nootka Cypress Cupressus nootkatensis
Distribution:	Northwest USA
Average Dried Weight:	495 kg/M3
Durability:	Durable
Janka Hardness:	( 2.58 kN )
Modulus of Rupture/Bending Strength	( 76.6 MPa)
Modulus of Elasticity/ stiffness:	( 9.79 GPa)
Crushing Strength:	( 33.5 MPa)

Seasoning:

• Dries fairly easily and without undue degrade.

## Characteristics:

- A pale yellow-coloured wood, with a fine even texture, which is straight grained.
- It has no appreciable colour when dry.
- Very stable.
- Acid resistant.

## Working Qualities:

- The timber is easily worked and finishes excellently.
- It can be glued, stained, polished and varnishes well.

Uses:

• High class joinery, boat building, cabinet work and veneers.

## Product Attributes:

- Consistent yellow colour.
- Straight grain.
- Machines and turns very well.
- Veneers available.
- Fixed widths Available

## **Product Limitations**

• Available in 50mm thickness only.